



PS SWELL MASTIC

PS SWELL MASTIC IS USED FOR

- Sealing rough and smooth construction joints of in-situ cast concrete.
- Sealing joints between pre-cast segments (e.g. manholes, box culverts, cable ducts and pipes).
- Sealing around steel H Beams.
- Sealing between rough surfaces (e.g. slurry walls) and concrete slabs.
- Bonding strips sealants to rough surfaces.
- Sealing around bolt spacers and void formers.
- On secant pile walls.

ADVANTAGES

- Solvent free.
- **PS Swell Mastic** can be applied to concrete, PVC, HDPE, steel etc.
- The excellent filling and adhesion properties of the product provide a first line filling of cracks and voids, even on lightly humid smooth or rough surfaces.
- In contact with water **PS Swell Mastic** will expand to 350% of its original volume.
- Flexible system, which adapts to the irregular surface of the substrate.
- Easy application with standard caulking gun.
- Durable: will exceed the construction's life.
- Has a good all round chemical resistance and can resist petroleum, mineral and vegetable oils and greases.
- **PS Swell Mastic** is approved for contact with potable water.

DESCRIPTION

PS Swell Mastic is a one component, polyurethane based, solvent free, hydro swelling mastic, supplied in cartridges and aluminium sausages, for the sealing of construction joints.

PS Swell Mastic cures and swells in the presence of moisture curing time depends on the temperature and humidity conditions i.e. curing time will reduce if the temperature are higher. **PS Swell Mastic** will become firm in 24-36 hours. Performance is not affected by the curing time.

APPLICATION

- **PS Swell Mastic** is preferably applied onto dust free concrete surface. The surface can be rough or smooth, moist or dry.
- Installation during heavy rain or in prolonged contact with water results in a premature swelling of the strip, which should be avoided.
- The mastic should cure for 24 hours before pouring concrete.
- Despite the fact that **PS Swell Mastic** has a very good adherence to the concrete, care must be taken as with all products of this type, not to pour the concrete directly on the product to avoid damaging of the applied sealant.

APPLICATION METHOD

Break the moisture proofing aluminium foil on the top of the cartridge and remove the seamer from the bottom. Cut the nozzle diagonally at the appropriate position. Place the cartridge in the caulking gun.



PRODUCT DATA SHEET

TECHNICAL DATA PROPERTIES

Property	Value	Norm
Solids	100%	Test DNC
Uncured		
Consistency	Gel/Paste	Test DNC
Density at 20	Approx, 1.45 kg/dm	Din 53504
Slump in vertical applications	5mm average 3mm	Boeing test
Hand dry (at 20 and 60% rel. humidity)	12h	Test DNC
Flash point	>130C	Pensky - martens method
Cured (7days at 25c, 10mm thick)		
Elongation at break	Approx 625%	DIN 53504
Tensile strength	Approx 2,2 n/mm2	DIN 53504
Resistance to hydrostatic pressure	Up to 150 metres of water column	Test DNC
Swelling capacity in contact with water	Swells to approx. 350% of its original dry volume	Test report KUL University

APPEARANCE

During application pasty, after curing rubbery.
Colour - White.

CONSUMPTION

The consumption of **PS Swell Mastic** per linear meter depends on the quality of the surface of the concrete.

Nozzle diameter	Length (cartridge)
3mm	20 – 25m
6mm	8 – 10m
8mm	4 – 5m
10mm	Approx.3m

PACKAGING

310ml cartridge	
12 per box	
1 pallet= 75 cardboard boxes	
Weight per cartridge	
• 0.55 kg gross	• 0.50 kg net

STORAGE

Minimum 12 months in a dry place at temperature between 5 degrees and 30 degrees. See shelf life information on the packaging.

CERTIFICATES/APPROVALS

WRAS drinking water approval - UK.